Converter for transforming 2K topcoats into 1K acrylic paints. When using the 2793 Acrylic converter for aerosols, no additional isocyanate hardener is required. The converted paints are prepared for filling into spray cans.

Substrate preparation

Technical data sheet 2025-2

2793 Acrylic converter for aerosols

Paint	By weight	100
2793 Acrylic converter for aerosols		15

Packaging

Product no.	Description	Volume/Weight	Packaging [pcs/box]
2793-1	/	1 L	6

Shelf life

Unlimited shelflife.

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.